

UNITED STATES PATENT APPLICATION

OF

KILIAN PETER HOCHREIN

AND

AMBROSIUS BAUER

FOR

COVER FOR CONTAINED AEROBIC

TREATMENT OF BIODEGRADABLE

MATTER

00401555-002200

TITLE OF THE INVENTION

10

15

20

25

30

35

40

During box composting, the wastes being composted are introduced to a structure similar to a horizontal silo. One or more sides of this structure, and especially the roof, are constructed with a cover tarpaulin so as to define a gas space above the fermenting bulk matter relative to the outside air. The box composting

- 5 structure includes appropriate ventilation devices, which permit full or partial flow of fresh air and/or recirculating air through the fermenting bulk, in order to supply the fermenting bulk with oxygen to maintain the fermentation process and to transport away liberated carbon dioxide and other fermentation gases.
- 10 The cover tarpaulin provides a barrier layer between the gas space and the outside air. An effective tarpaulin should protect the fermenting product from extreme dry-up in dry and hot climatic conditions. It should also protect the fermenting matter from wetting during precipitation when installed in a structure so that the tarpaulin is the uppermost shell. Both dry-out and excessive wetting would adversely
- 15 affect the fermentation process and results.

- Large amounts of precipitation also lead to disproportionately high volumes of seepage with a high load of dissolved or suspended organic substances. This seepage is a significant environmental hazard that is very costly to dispose of in a controlled
- 20 manner.

- Moreover, the cover tarpaulin should serve to retain undesired odorous substances that emerge from the fermenting product in significant amounts. Adequate odor retention is frequently crucial for obtaining the necessary permits for
- 25 biological waste treatment installations. This is particularly true in Germany and many other European countries, where there are monitoring and regulative procedures regarding odor emissions and imissions.

- The cover tarpaulins, in many cases, should also ensure that no health-
- 30 relevant microbes or spores are emitted from the fermentation process. The cover tarpaulin should also prevent the surface of the fermenting material from being excessively cooled. This would restrict the aerobic fermentation process and prohibit complete destruction of weeds and pathogens as required by regulations in many countries. Covering the fermenting material with an air permeable tarpaulin and
- 35 aerating with ventilation devices achieves weed and pathogen destruction without having to turn and mix the fermenting bulk several times during the process. Thus, covering significantly reduces emissions as compared to open heap composting, as well as it saves operating cost. By protecting the fermenting product from daylight, especially UV radiation, the surface of the fermented product can be populated by UV-
- 40 sensitive fungi, which are crucial to the process in individual phases of fermentation.

00401505-002200

10

15

20

35

40

- 5 Therefore, there is an optimum window of air permeability of the cover tarpaulin that needs to be maintained. The lower limit is essential to keep cost down while opening a reasonable process window. The upper limit ensures control of odor emissions as well as a stable and even fermentation process by avoiding formation of channel flows inside the fermenting bulk matter and maintaining a reasonably
- 10 accurate correlation between pre-settings of the ventilation devices and resulting air exchange rates.

- Experience with covers for box composting shows that during cold weather and/or precipitation the effective air permeability of the known tarpaulins
- 15 diminishes sharply and formation of seepage and condensate in the fermentation space rises sharply. This means that the fermentation process may not function satisfactorily during the winter months in temperate latitudes or cold climates when using known tarpaulins. Large amounts of organically loaded seepage waters are then formed, which must be sent to costly seepage water treatment and therefore have an unfavorable effect
- 20 on the operating costs of the installation. Also, under these conditions, the quality of the fermented product is typically compromised and requires added effort and cost in post-treatment.

- Commonly used covers for box composting include multi-layered
- 25 textile laminates according to the following structures; textile woven fabric or non-woven on the outside – microporous intermediate layer – textile woven fabric, non-woven or knitted fabric on the inside. The textile laminates used for box composting so far have been largely identical to the laminates used for covering compost heaps. Such laminates for covering heaps are, for example, described in the German Patent DE
- 30 4231414 A1.

- The textile/non-woven layers of these tarpaulins serve for achievement of the necessary mechanical properties (tensile strength, abrasion resistance, weathering protection, etc.), whereas the microporous layer serves as the
- 35 barrier for odors, germs and precipitation water. At the same time, however, the microporous layer also determines the air and water vapor permeability. Due to the geometry and thermodynamics of the box composting process, the requirements for box cover laminates are distinctly different from those for heap covers.
- 40 In order to cover a heap of compost, typically 1.0 to 2.0 m² of tarpaulin are used for every m³ of fermenting bulk matter. In contrast, the geometry of composting boxes only allow between 0.5 to 1.0 m² of tarpaulin for every m³ of fermenting bulk matter.

09401505-092299

- 5 Because the specific oxygen demand of the fermenting bulk matter is largely independent from the composting setup, as long as it is covered, box composting laminates need to exhibit an air permeability that is significantly higher than heap composting laminates. DE 4231414 A1 claims an air permeability of 1 to 15 l / m² / sec at 10 mbar. This is equivalent to 0.7 to 10 m³ / m² / h at 200 Pa. 200 Pa is the maximum
- 10 desirable pressure head for box composting in terms of cost control. Commercially available heap composting laminates tested for air permeabilities were found to be in the range of 0.5 to 3 m³ / m² / h at 200 Pa pressure gradient applied perpendicular to the tarpaulin..
- 15 Due to the specific requirements mentioned for box composting, air permeability at 200 Pa needs to exceed 10 m³ / m² / h to allow the favored intermittent aeration mode throughout the range of air exchange rates necessary to operate and effectively control the process.
- 20 During experiments using a cover with an air permeability of 80 m³/m²/h measured at 200 Pa, no pressure build-up greater than 50 Pa could be observed in the gas space underneath the tarpaulin. This was true over the full range of relevant air exchange rates while using a comparatively fine-grain bulk material. Even with coarse fermenting bulk feedstock likely to exhibit the least tendency to form channels of air flow, such as
- 25 shredded bark or wood chips, air permeability should not exceed 100 m³ / m² / h at 200 Pa to avoid formation of channels and ensure pressure build-up underneath the tarpaulin. Preferably, air permeability should be below 50 m³/m²/h at 200 Pa. This will ensure that the process is controllable even at low air exchange rates.
- 30 Despite a temperature of the fermenting product of up to 80°C or so , the temperature in the gas space beneath the tarpaulin is closely linked to ambient temperature. The gas that emerges from the fermenting product into the gas space is saturated with moisture. At outside temperatures below 10°C, significant condensation and mist formation occurs in the gas space, with the result that the textile inside of the
- 35 known tarpaulins such as described in DE 4231414 A1 become liquid-drenched. This diminishes the air permeability of the laminate. Since the aqueous condensate typically comprises a number of surface active organic compounds, it exhibits a stronger tendency than water to wet the microporous layer, at least to wet the surface of the porous layer that faces the fermenting matter. This can occur, in particular, when after
- 40 some time organic condensate constituents have deposited in the microporous layer altering the surface properties of the microporous structure. This reduces wetting

- The surface tension of a condensate collected from a pilot scale box composting trial was analyzed to be 42 mN/m, which is considerably lower than water. It is known that an acceptable level of repellency for liquids with surface tensions around 40 mN/m is present on a surface that exhibits an Oil Rating equal to or greater than 1.
- Aging of the microporous layer often occurs within a few months of field use if the porous layer also consists of polymers susceptible to degradation caused by weather, UV-light, hydrolysis or microbial attack, for example, a polyurethane coating or polyethylene membrane such as described in DE 4231414 A1. This type of aging also frequently includes that water- and rainproofness of such covers are compromised. All this results in operating problems and increased cost.
- A similar reduction in air permeability occurs when the textile outside of the cover tarpaulin is drenched by precipitation water. The resulting water layer, on the one hand, leads directly to a reduction in air permeability of the outside layer. On the other hand, the cooling effect of the precipitation causes an increase in condensation level in the gas space, so that increased moistening of the tarpaulin inside occurs with a corresponding reduction in air permeability. Wetting of the outside cannot be permanently prevented, according to experience, by water-repellent textile finishing since these finishings do not exhibit adequate weather resistance.
- Furthermore, DE 4231414 A1 does not specify any water entry pressure. It is known that in order to keep precipitation out, a minimum water entry pressure greater than 20 kPa, preferably greater than 50 kPa needs to be maintained over the lifetime of the tarpaulin.
- It is known that many feedstocks for composting or aerobic waste treatment, especially from source-separated collection of household organic wastes, contain amounts of moisture that are not acceptable for any soil amendment product nor for any uncontained processing. Any contained aerobic treatment must therefore have the potential to achieve a significant reduction in moisture of the fermenting bulk material. In box composting, moisture can either diffuse through the tarpaulin or be conveyed out with the air flow permeating through the tarpaulin. Diffusion depends on the temperatures and the gradient of water vapor partial pressure perpendicular to the tarpaulin, and is limited by the Resistance to Moisture Vapor Transmission (Ret) of the

- 5 tarpaulin. Convection is driven by the total pressure gradient perpendicular to the tarpaulin and is limited by the air permeability of the cover.

- Cover materials as described in DE 4231414 A1 analyzed have exhibited Ret-values between 13 to 40 m² Pa/W. Especially during cold ambient conditions, this high
- 10 resistance to water vapor permeation does not allow enough moisture out of the system. Increasing air permeability of the cover to a sustained higher level alone will not provide a least-cost operating mode under cold/wet conditions. As long as diffusive moisture vapor transmission is impaired by high Ret, a massive increase in air flow would be needed to convey out excessive moisture. This would increase operating cost
- 15 proportionally as well as the risk of cooling the bulk matter too much by introducing excessive volumes of cold air. With the existing covers, such high airflows are not feasible at the maximum applicable pressures, because the air permeability of the covers is too low. Therefore, a cover that has an increased air permeability according to this invention has to have Ret-values below 15 m² Pa / W, preferably below 10 m² Pa/
- 20 W are in order to increase diffusion and minimize air flow to the amount needed to supply only the oxygen demand of the fermenting matter. Reducing the air flow also minimizes the emission of odorous substances that are conveyed out with the gas stream permeating through the tarpaulin.
- 25 A growing concern with fermentative treatment of organic wastes is the emission of potentially pathogenic microbes such as viable bacteria, fungi, their spores and some of their fragments. It is known from biology and hygiene practice that these germs occur in particle sizes typically greater than 0.5 micrometers. It is therefore reasonable to believe that any system that retains more than 98% of the particulates greater than 0.5
- 30 micrometers from a gas stream provides sufficient protection. It is known from membrane filtration of dust from gas streams that a porous film with a mean pore size of 10 micrometers allows retention of more than 98% of particulates greater than 0.5 micrometers. Furthermore, it is known from membrane vents installed into medical devices that these vents are certified to provide sterile filtration for air regarding HIV
- 35 and Hepatitis viruses as long as the pore size of the porous layer measured as Coulter MFP is below 3 micrometers.

SUMMARY OF THE INVENTION

- 40 The cover materials of this invention overcome the deficiencies of present cover materials used in aerobic treatment of biodegradable matter.

The cover tarpaulins of this invention provide:

- 5
1. Optimum specific air permeability at low overpressures maintained under a wide variety of climatic conditions: This ensures good and even oxygen supply into the fermenting bulk matter at low operating costs and minimal investments for structural gas-proofing.
 - 10 2. High water vapor permeability, in order to dry moist types of waste (for example, biocans) quickly to the moisture content at which a subsequent treatment becomes feasible in simple setup without any means of containment minimizing investment and operating cost.
 - 15 3. Reliable sustainment of operationally relevant properties of the laminate, in order to keep maintenance and operating costs, as well as environmentally relevant emissions, to a minimum, and ensure stable, controllable operation independent of ambient conditions.
 - 20 4. High odor retention in the gas space beneath the tarpaulin: This makes installations with high throughputs eligible for use in odor emission-sensitive locations.
 - 25 5. Retention of microbes, spores and/or refractory microbial matter, in order to minimize infectious and sensitizing biological emissions.
 6. Waterproofness to the degree that no precipitation can ingress through the tarpaulin when installed so that the cover is directly exposed to the atmosphere.
 - 30 7. An adequate tensile strength to withstand the forces from internal overpressure as well as loads caused by wind, rain and snow wherever the cover is installed.
- These goals are achieved by the covers of the invention. The covers
- 35 comprise a laminate of
- 1). a porous polymeric layer adhered to
 - 2). at least one selected woven or knit or nonwoven fabric,
- in which the laminate has
- a) an air permeability of between 10 and 100 m³/m²/hour at 200 Pa pressure
 - 40 difference, preferably 15 to 50 m³/m²/h at 200 Pa
 - b) an Ret less than 15m² *Pa /W, preferably between 2 and 10 m²Pa/W

09401595:002299

- 5 In a preferred embodiment of the invention providing waterproofness against precipitation and retention of pathogenic or sensitizing microbial emissions, the laminate will have a water entry pressure of at least 20 kPa, preferably greater 50 kPa, and water entry pressure can be as high as 1 MPa, and the porous layer will have a pore size of between 0.2 to 10 μm , preferably 0.3 to 3 μm as determined by the Coulter
- 10 Test described below. A woven fabric is chosen to provide tensile strength of the laminate exceeding 1000N/5 cm, preferably greater 2000N/5cm.

- In use, the porous layer side of the laminate faces the fermenting matter, while the fabric is outermost and is exposed to the atmosphere. However, in cases where
- 15 mechanical stresses may apply to the side of the laminate facing the fermenting matter, a second fabric layer may be applied to the inside, preferably an openly knitted fabric made from coarse filaments so to minimize capilarity on the side facing the fermenting matter.

20

BRIEF DESCRIPTION OF THE DRAWINGS

- Figure 1 shows a SEM cross section of laminate 1 as described in the examples. The porous layer (bottom) is shown adhered to a woven fabric.

25

Figure 2 shows a SEM cross section of laminate 3 as described in the examples. The porous layer (middle) is shown adhered between a woven fabric and a knitted fabric (bottom).

- 30 Figure 3 shows a SEM cross section of laminate 4 as described in the examples. The oleophobiclly coated porous layer (bottom) is shown adhered to a woven fabric.

- Figure 4 shows a SEM cross section of laminate 5 as described in the examples. The oleophobiclly coated porous layer (middle) is shown adhered between a woven fabric
- 35 (top) and a knitted fabric (bottom).

DETAILED DESCRIPTION OF THE INVENTION

- The covers of this invention combine the proper degree of air permeability with a low resistance to evaporative transmission Ret. Due to this combination, the biological processes of aerobic degradation can be controlled through adjusting the air exchange
- 40

- 5 rate over a wide range without compromising the control of moisture transmission, more specifically the control of any drying processes of the fermenting matter.

This is especially important at low ambient temperatures, typically 5°C or less, that do not permit significant amounts of moisture to be convectively transported through the laminate by the permeating gas stream. Any air exchange rate resulting in a significant convective moisture transport through the cover would cause unwanted cooling of the fermenting material, because large volumes of cold ambient air would be induced into the fermenting material. Under these conditions, the moisture transmission needed to achieve the process goal needs to be realized predominantly by diffusion. This is only possible at Ret-values below 15 m²Pa/W, preferably less than 10 m²Pa/W.

When the convective gas stream is not needed to control moisture transmission, it can be optimally adjusted to control the aerobic process and thus optimize product quality, reduce dwell time or minimize operating cost.

20 The low resistance to evaporative moisture transport Ret of the covers of this invention is achieved by omitting or minimizing the inside textile layer needed in heap composting for mechanical protection of the porous layer.

25 In applications where extremely low Ret is required, this may be achieved by minimizing the thickness of the fabric layer through the use of high tenacity fibers such as, but not limited to carbon fiber, and polyamide fiber.

In a preferred embodiment of this invention, where the cover material is used in box composting, the retention of microbial pathogens and irritants is achieved by using a mean pore size of the porous layer no greater than 10 micrometers as defined by the Coulter measurement, preferably smaller than 3 micrometers. Exclusion of rain and other precipitation infiltrating into the fermenting material is achieved by providing a cover material that has a Water Entry Pressure greater than 20 kPa, preferably greater 35 50 kPa.

In a preferred embodiment of this invention, wetting of the inside of the cover tarpaulin is prevented or reduced by not having a textile inner layer that is present in prior art covers, or by using a sufficiently open knitted fabric that is treated to become oleophobic with Oil Rating greater 1, preferably greater 5, by processes known 40 in the art of textile converting. This inside textile layer may also be replaced by a wide-mesh net or grid, which can be sewn to the actual tarpaulin cover or clamped to it. Such

- 5 net or grid material may also be bonded to the porous layer by adhesive or thermoplastic means evenly over its entire surface.

An Oil Rating of 1 can be achieved by using a porous membrane made of expanded Polytetrafluoroethylene. Also, the porous structure of the layer can be treated to make it oleophobic enough to have an oil rating > 1 , so that wetting and contamination with organic substances is durably prevented. Such treating and agents are described in German Patent Application P 43083692. Preferred are oil ratings greater than 1; ideally an Oil Rating greater than 5 would provide a very good liquid repellency and resistance against contamination with organic substances. Oil ratings equal to or greater than 5 may be achieved on knitted fabric using commercially available fluorocarbon coatings known in textile converting.

Excessive wetting of the outside fabric of the cover by rain can be prevented by using an inherently hydrophobic polymeric material for the yarn used to make the fabric. Such polymers include, for example, Polypropylene, Polyacrylate, Polytetrafluoroethylene or other Fluoropolymers. The yarn is woven so that maximum liquid repellency is achieved without any significantly adverse effect on air permeability.

In a preferred embodiment of the invention, operational reliability of the compost installations is increased substantially and the operating costs are minimized because the formation of an obstructive layer of liquid on or within such covers is avoided or minimized. This is done by using a water-repellent fabric as the outer material and using a hydrophobic/oleophobic or hydrophobically/oleophobically coated porous layer facing the fermenting product, as well as omitting or minimizing any dense or capillary textile on the side facing the fermenting product. If a textile layer is used on the side facing the fermenting product, it may be treated to provide water and oil repellency. As a result the, covers of this invention maintain a high air permeability under colder and wetter weather conditions than previously possible.

The porous polymeric layer can be made of a polymer which is inherently hydrophobic, such as a fluoropolymer, or can be a membrane not inherently hydrophobic but which has been treated with a water- and oil-repellent polymer to make it hydrophobic and oleophobic. The porous layer can be made of any of a number of synthetic polymers which can withstand long-term continuous contact with liquid water, preferably being resistant against degradation by UV-light and microbial attack. Polymers such as, but not limited to, polyethylene, polypropylene, polyurethane or

- As stated earlier, the structure defining the pores of the porous layer and/or the porous support layer of the porous cover can be coated with a water- and oil-repellent organic polymer. No particular limitations are imposed on the polymer as long as it provides acceptable levels of water- and oil-repellency, and can be applied so as to form a coating on at least a portion of the structure defining the pores of the porous layer or support material, without causing substantial reduction of the pore volume of the layer or support material or significantly diminishing air flow through the materials. Preferred polymers or copolymers are those having recurring pendent fluorinated organic side chains, or those having fluorine-containing main chains.

Even though the porous layer of the cover can be made of an inherently hydrophobic polymer, it can be desirable to treat the layer with a water- and oil-repellent material to increase its oil-repellency. The reason for this is that water-soluble compounds such as alcohols, fatty acids, lipids, aromatic compounds, water-soluble oils and the like, are typically present in the fermenting bulk organic matter, or may be present in the gases generated by decomposition of the materials. Such compounds have been detected in the gas phase or dissolved in the water condensing on the inside surface of the cover. They can preferentially elute from the condensate to wet and coat the porous surfaces, thus altering the surface free energy of the structure defining the pores and making the layer wettable by liquid water. Liquid water, preferably in the form of condensate containing said surfactant organic compounds, can

5 then penetrate into the pores of the layer, occupy portions of the pore volume, and significantly reduce air and gas permeability through the membrane. Even without penetrating into the pores, such surfactants facilitate wetting of the outer surface of the membrane. This may produce a superficial water layer on the surface of the porous layer. This superficial water layer obstructs gas entry reducing air permeability.

10

By coating the surfaces of the structure defining the pores so as to make the surfaces oleophobic, the surfactants are prevented from contaminating the surfaces defining porous structure and the condensate is prevented from wetting the surfaces defining the porous structure or the surface of the porous layer.

15

The layer described and the outward fabric, preferably a polyester or polypropylene or polytetrafluoroethylene woven fabric, are bonded to each other by lamination means. This can be done by softening, i.e., partially melting, the fibers of the textile if made of thermoplastic polymer and bonding it to the membrane, or it may
20 be done using adhesives applied to adhere between fabric and membrane. The adhesives typically used are from the classes of polyurethanes, silicones or polyacrylates, preferentially cross-linked, UV-stable reactive polyurethane hotmelts. Adhesive application can be achieved by means of printing, smear coating or melt blowing. Also, hot-melt adhesives in the form of webs may be used. Preferred is the
25 application of said reactive polyurethane hot-melt adhesives by gravure-dot or gravure-grid lamination. Alternatively, the porous layer may be coated onto the fabric in the form of water-based or solvent based latex or dispersion or a reactive solution or by a phase inversion process using any of the mentioned polymers suitable for the formation of the described porous layer.

30

The textile face of the laminate thus produced may subsequently be treated for durable water repellency by applying an aqueous base coating of water repellent chemical consisting of fluorocarbons or silicones, preferably fluorocarbons with cross-linking agents such as to maximize durability of water repellent effect.

35

TEST DESCRIPTIONS

Air Permeability - Gurley Number Method

The resistance of samples to air flow was measured by a Gurley
40 densometer (ASTM D726-58) manufactured by W. & L.E. Gurley & Sons. The results are reported in terms of Gurley Number which is the time in seconds for 100 cubic

- 5 centimeters of air to pass through one square inch of a test sample at a pressure drop of 4.88 inches of water.

Air Permeability - Textest Method

- 10 The Textest FX 3300 air permeability tester with a 100 cm² head. This device is designed and used in accordance with DIN-ISO-EN 9237 (1995). The pressures used in this application range from 100 to 1000 mbar. The pressure is selected so that an airflow within the measuring range of the apparatus is achieved. The sample is pulled
- 15 tight onto the sample holder and clamped into the apparatus. A green LED indicates when to take the reading from the digital display. The first measurement is done with the air permeable sample by itself in the sample holder, the second is done with a air impermeable sheet on the permeate side of the sample clamped into the device in addition. This second measurement is done to determine the lateral leakage of air through the voids in the textile structure that cannot be sealed by clamping. The actual
- 20 air permeability is then derived by subtracting the leakage flow from the total flow measured in the first measurement. Depending on the pressure used, the result is then linearly converted to the appropriate air permeability at 200 Pa.

- 25 A total of 5 samples distributed over the width of the material is necessary.

Oil Rating Measurement

- Oil rating is measured according to ISO 14419 (September 1998). Oil rating is a manual/visual measurement conducted to quantify the wetting behavior of solid, porous or textile surfaces. It uses a set of aliphatic oils that offer a wide range of surface
- 30 tensions. The Oil Rating is given according to the highest ranking of these oils that does not wet the surface. The liquids related to the ratings are:

- | | | |
|----|---|---|
| | 0 | None (fails white mineral oil) |
| | 1 | Paraffin Oil High Viscosity |
| | 2 | Mixture from 65 % Paraffin Oil HV and 35% n-Hexadecan |
| 35 | 3 | n-Hexadecan |
| | 4 | n-Tetradecan |
| | 5 | n-Dodecan |
| | 6 | n-Decan |
| | 7 | n-Octan |
| 40 | 8 | n-Heptan |

- 5 Five sessile drops are placed onto a horizontal sample with a distance of 4 cm each and at a 45° angle. Observation time is 30 sec +/- 2 sec, after which each drop is compared with the image given in the mentioned ISO standard. If no wetting of or penetration into the sample is observed, the next higher rated liquid is employed. This process is repeated until wetting or penetration are observed within the 30 sec testing time. A
- 10 rating is failed when three or more out of the five sessile drops exhibit complete wetting or when capillary effects are observed that annihilate the contact angle between liquid and surface. The Oil rating is given according to the rank of the last liquid that passed for all five drops. In marginal cases a half note may be given, i.e. 3.5. This is described in detail in the ISO-standard.

15

Pore Size Measurement

Pore size measurements are made by the Coulter Porometer™ manufactured by Coulter Electronics, Inc., Hialeah, FL.

- 20 The Coulter Porometer is an instrument that provides automated measurement of pore size distributions in porous media using the liquid displacement method described in ASTM Standard E1298-89.

- 25 The Porometer determines the pore size distribution of a sample by increasing air pressure against one side of a sample which has its pores filled with a liquid, and measuring the resulting flow. This distribution is a measure of the degree of uniformity of the membrane (i.e., a narrow distribution means there is little difference between the smallest and largest pore size). It is found by dividing maximum pore size by the minimum pore size. The Porometer also calculates the mean flow pore size. By
- 30 definition, half of the fluid flow through the porous material occurs through pores that are above or below this size.

All quotations of pore sizes refer to an average Mean Flow Pore Size (MFP), unless explicitly stated.

35

- However, not all conceivable cover laminate materials can be measured using the described Coulter method. This is due to the mechanical structure of some of these laminates and porous layers. In such cases, pore size measurement may be done using microscopy. By evaluating cross sections of either light or scanning electron
- 40 micrographs with commercially available image processing software, the pores of the porous layer can be measured geometrically. The geometrical pore width equivalent to

- 5 the Mean Flow Pore Size according to the invention shall have a statistical confidence interval of 90 per cent with regards to a 10 m² sample.

Tensile Strength

- The tensile strength of the laminate samples is measured according to ISO 1421 using
- 10 an INSTRON Type 4466 tensile tester, equipped with a 10 kN cartridge and computerized data acquisition in a room conditioned to ISO 2231 standard climate (20°C, 65% relative humidity). For each material, five samples are tested in machine and transverse direction each. Sample width is 50 mm, length at least 350 mm and sample is provided yarn-straight. The distance between the clamps is 200mm, load
- 15 limits, extensions and speed is controlled by the PC. The laminate sample is pretensioned with 2N if sample weight is below 200 g/m², above this 5N pretension is used.

Water Entry Pressure Test (WEP)

- 20 The water entry pressure test is a hydrostatic resistance test which consists essentially of forcing water against one side of a test piece and observing the other side of the test pieces for indications of water penetration through it.

- The test specimen was clamped and sealed between rubber gaskets in
- 25 a fixture that holds the test pieces. The fabric surface of the test specimen was in contact with the water and the other side faced upward, open to the atmosphere, for close observation. Air was removed from inside the fixture and pressure was applied to the inside surface of the test pieces as water was forced against it. The water pressure on the test piece was increased gradually and the upward-facing surface of the test piece
- 30 was watched closely for the appearance of any water forced through the material. The pressure at which water appears on the upward-facing surface is recorded as the water entry pressure.

Resistance to Moisture Vapor Transmission Ret

- 35 The Ret value is a specific material property of sheet-like structures or material assemblies, which determines the "latent" vaporization heat flux through a given surface resulting from an existing steady-state partial pressure gradient.

- The water vapor transmission resistance is determined using the
- 40 Cup Method using the FIH method which is described in the standard test regulations No. BPI 1.4 dated September 1987 issued by the Bekleidungsphysiologisches Institut e.V. Hohenstein, Germany.

5

EXAMPLES

Several laminates were produced using two different experimental membranes obtained from W.L. Gore & Associates of Newark, Delaware, USA.

10

Both membranes were produced based on an expanded polytetrafluoroethylene membrane with an average MFP of 0.8 micrometers having a thickness of approximately 50 micrometers and an area weight of approximately 15 grams per square meter.

15

Membrane 1 was pure expanded PTFE described above. For the examples described herein, a total of three different production batches of the experimental membrane were produced with similar physical properties

20

Membrane 2 was made by using membrane 1 and coating the surfaces defining the porous structure of the membrane with approximately 5 grams per square meter of a fluoroacrylate containing pendant perfluorinated side groups, thus achieving an Oil Rating of the coated membrane surface of 8. Such fluoroacrylates can be obtained from fluorochemical manufacturers such as E.I. DuPont, Asahi Glass Chemical or Hoechst

25

AG.

30

Laminate 1 was made laminating Membrane 1 to a layer of 220 g/m² dyed 1100 dtex high-tenacity polyester 10/10 plain weave fabric obtained from C. Cramer & Co., Heek-Nienborg, Germany to side to be facing away from the fermenting matter. An SEM of a cross section of laminate 1 is shown in figure 1.

Laminate 2 was made laminating Laminate 1 to the same but undyed polyester plain weave to the side to be facing the fermenting matter.

35

Laminate 3 was made using Laminate 1 and laminating to it a 30 g/m² polyamide mono-filament tricot knit fabric obtained from S & T Barnstaple Ltd., Barnstaple, North Devon, GB onto the side to be facing the fermenting matter. A cross-section of laminate 3 is depicted in the SEM of Fig.2

40

Laminate 4 was made laminating Membrane 2 to a layer of 220 g/m² polyester 10/10 plain weave fabric obtained from C. Cramer & Co., Heek-Nienborg, Germany to side to

0041506: 002200

- 5 be facing away from the fermenting matter. A cross section of laminate 4 is depicted in the SEM in figure 3.

Laminate 5 was made using Laminate 4 and laminating to it a 30 g/m² polyamide monofilament tricot knit fabric obtained from S & T Barnstaple Ltd., Barnstaple, North
10 Devon, England on to the side to face the fermenting matter. A cross section of laminate 4 is depicted in the SEM in figure 4.

All lamination was achieved with dot-gravure print lamination using a cross-linked polyurethane adhesive obtained from W.L. Gore & Associates of Newark, Delaware,
15 USA, at an average adhesive laydown of 8 g/m² for Laminate 2 and an average laydown of 16 g/m², respectively 8 g/m² on each of the two fabric layers, for Laminates 1,3,4,5.

Laminate 2 was produced in two instances in a continuous lamination process using two
20 subsequent printing/laminating steps comprised in a single machine. Laminates 1, 3, 4 and 5 were manufactured in a single lamination run during which the fabrics and membranes were switched accordingly in order to obtain the described laminates

In case of laminates 4 and 5, the side of the membrane to which the fluoroacrylate
25 coating had been applied was laminated facing to the side to face toward the fermenting matter.

Subsequently to lamination, all laminates were dip coated with an aqueous based proprietary mix of commercially available fluorocarbons so that both fabric sides of the
30 laminates were coated to obtain water and oil repellency of the fabric layers. Such mixes of fluorocarbons are known art in textile converting.

00401505 0022200
0022200 50510460

662260-19 56510460

Laminate	Air Permeability [m ³ /m ² /h] @200Pa	Ret [m ² /Pa/W]	Pore Size [μm Coulter MFP]	Tensile Strength [N/5cm]	WEP [kPa]	Oil Rating
1	43.1	6.2	0.7	2596	68	1.5
2	16.6	13.7	0.7	4023		
3	17.2	8.8	0.7	2622	69	1.5
4	38.9	5.8	0.7	2796	47	8
5	20.3	7.3	0.7	3003	58	5.5

Oil rating in this table refers to the side of the laminate facing towards the decomposing material.